PCT

÷

WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 5:
A61B 17/064

(11) International Publication Number: WO 92/13491
(43) International Publication Date: 20 August 1992 (20.08.92)

(21) International Application Number: PCT/US92/00209

(22) International Filing Date: 8 January 1992 (08.01.92)

(30) Priority data: 653,353 6 February 1991 (06.02.91) US

(71) Applicant: MINNESOTA MINING AND MANUFAC-TURING COMPANY [US/US]; 3 M Center, Post Office Box 33427, Saint Paul, MN 55133-3427 (US).

(72) Inventors: VIDAL, Claude; REDMOND, Russell, J.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US).


(74) Agents: HOHENSHELL, Jeffrey, J. et al.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US).

(81) Designated States: AT (European patent), BE (European patent), CA, CH (European patent), DE (European patent), DK (European patent), ES (European patent), FR (European patent), GB (European patent), GR (European patent), IT (European patent), JP, LU (European patent), MC (European patent), NL (European patent), SE (European patent).

Published

With international search report.

(54) Title: IMPROVED SURGICAL HARDWARE WITH BACTERIOSTATIC SILVER COATING, AND METHOD OF USING SAME



(57) Abstract

A staple, wire suture, clip, or other item of surgical hardware is disclosed which can be used to close a wound, made from a high strength metal to have a low profile design to minimize interference and disturbance of the wound, and having a bacteriostatic silver coating to reduce the risk of wound infection from the hardware. A method of closing surgical wounds with reduced risk of infection is also disclosed, the method includes the steps of closing the wound with a staple, wire suture, clip, or other item of surgical hardware made from a high strength metal that has a silver coating.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

TA	Austria	FI	l-inland	MI	Mali
AU	Australia	FR	France	MN	Mongolia
BB	Burbados	GA	Gabon	MR	Mauritania
BE	Belgium	GB	United Kingdom	MW	Malawi
BF	Burkina Faso	GN	Guinea	NI.	Netherlands
BG:	Bulgaria	GR	Greece	NO	Norway
BJ	Benin	HU	Hungary	PL	Poland
BR	Brazil	1E	Irckind	RO	Romania
CA	Canada	IT	Italy	RU	Russian Federation
CF	Central African Republic	9L	Japan	SD	Sudan
CG	Congo	KP	Democratic People's Republic	SE	Sweden
CH	Switzerland		of Korea	SN	Senegal
CI	Cote d'Ivoire	KR	Republic of Korea	SU	Soviet Union
CM	Cameroon	LI	l iechtenstein	TD	Chad
CS	Czechoslovakia	LK	Sri Lanka	TG	Togo
DE	Ciermany	LU	Luxembourg	US	United States of America
DK	Denmark	MC	Monaco		
EC.	Sredn	MG	Madagascar		

10

15

20

25

30

IMPROVED SURGICAL HARDWARE WITH BACTERIOSTATIC SILVER COATING, AND METHOD OF USING SAME

5 BACKGROUND OF THE INVENTION

This invention relates to surgical hardware of the type used to close wounds, and to an improved method of closing wounds using such hardware.

Various items of metal hardware have been developed to assist in closing wounds. At one time such hardware was made from solid silver. However, because of silver's high ductility and relatively low strength, silver hardware had to be made very coarse to have adequate mechanical properties. For many applications solid silver hardware was objectionably coarse. High strength metals such as stainless steel and titanium, permit more slender, clinically desirable hardware designs, and have for decades been the state of the art materials for surgical hardware.

Wound infection is always a serious concern because of its system-wide effect and retardation of normal wound healing, but when surgical hardware is required and used there are additional potential complications from wound infection including dehiscence or splitting of the wound, leakage from the wound, and formation of adhesions. While conventional steel and titanium hardware can be sterilized, it does not appear to have significant bacteriostatic effect, and may actually promote infection compared with other materials. Nevertheless, because these high strength metals permit the manufacture of such small, high strength hardware, these metals are still widely used.

SUMMARY OF THE INVENTION

35 The present invention provides an improved item of surgical hardware that provides the strength and compact size of a high strength metal such as stainless steel or titanium, and bacteriostatic properties to reduce the risk of wound infection. This hardware allows wounds to be

Έ

5

10

15

20

25

30

neatly and effectively closed, and provides some bacteriostatic action that reduces the risk of many of the complications encountered in the use of surgical hardware.

The invention relates to a staple, wire suture, clip, or other item of surgical hardware used in closing wounds. Generally, the surgical hardware constructed according to the principles of the present invention comprises an item of surgical hardware that is made from a high strength metal, for example stainless steel or titanium, and which has a silver coating. The silver coating may be either silver plating, or a coating of silver salt. Generally the method of closing wounds according to the present invention comprises closing the wounds with surgical hardware made from a high strength metal and which has a silver coating.

The hardware of the present invention provides all of the advantages of being constructed from a high strength metal, including high strength and compact size, and the additional benefit of bacteriostatic action which helps to reduce the risk of complications resulting from the use of the hardware. The compact design permitted by the present invention ensures that the hardware has sufficient strength to hold the wound closed, and a sufficiently compact size that it does not unduly disturb the wound site or interfere with healing. The cost of manufacturing hardware according to the principles of the present invention is only manufacturing of than the cost higher marginally The method of this invention conventional hardware. provides a way to close wounds with reduced risk of infection and complications.

These and other features and advantages will be in part apparent and in part pointed out hereinafter.

BRIEF DESCRIPTION OF THE DRAWINGS

35 FIGURE 1 is a perspective view of an internal (soft tissue) staple constructed according to the principles of this invention;

5

10

15

20

25

30

35

FIGURE 2 is a perspective view of a skin staple constructed according to the principles of this invention;

FIGURE 3 is a perspective view of a fascia staple constructed according to the principles of this invention;

FIGURE 4 is a. perspective view of a vascular staple constructed according to the principles of this invention;

FIGURE 5 is a perspective view of a vascular clip constructed according to the principles of this invention;

FIGURE 6 is a perspective view of a wire suture constructed according to the principles of this invention; and

FIGURE 7 is a cross-sectional view of the wire suture, taken along the plane of line 7-7 in Figure 6.

Corresponding reference numerals indicate corresponding parts throughout the several views of the drawings.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

Surgical staples constructed according to the principles of the present invention are indicated generally as 20, 22, 24, and 26 in Figures 1 - 4. A surgical clip constructed according to the principles of the present invention is indicated generally as 28 in Figure 5. A wire suture constructed according to the principles of the present invention is indicated generally as 30 in Figure 6. Although the present invention is described with respect to staples, clips, and sutures, the invention is not so limited and relates to any item of surgical hardware of the type used to close wounds.

The staples 20 - 26, the clip 28, and the suture 30 are made from a high strength surgical metal such as a stainless steel or titanium. Because they are constructed of a high strength material, these items have superior strength, and more importantly they can be designed to be small and compact so that they do not unnecessarily disturb the wound or interfere with proper healing. However, unlike any prior art item of surgical hardware, the staples 20 - 26, the clip 28, and the wire suture 30 have a silver coating. This is best shown in Figure 7 where the suture is shown as

5

10

15

20

25

30

comprising high strength surgical metal 32 with a silver coating 34. The silver coating provides a bacteriostatic action that inhibits infection. Thus infection is less likely to propagate when the surgical hardware of the present invention is used, and thus there is a reduced risk from infection-related complications from the use of such hardware.

The silver coating may be silver plating applied by a hot dip or electro-deposition process, or some other method. Alternatively, the coating may be a silver salt applied to the exterior of the item of hardware, for example silver nitrate, or silver-zinc allantoinate.

The method of the present invention relates to an improved method of closing surgical wounds with reduced risk of infection. The method comprises the step of closing the wound with a staple, wire suture, clip or other item of surgical hardware made from a high strength metal that has a silver coating.

The bacteriostatic effect of the hardware of this invention was tested by introducing a silver coated staple according to the principles of this invention, a stainless steel staple, and titanium staple into two difference agar media: Trypticase Soy Sheep Agar and Mueller Hinton Agar. Each of the staples was screened against staph aureus, Escherichia coli, Pseudomonas aeriginosa, The plates were inoculated with a standard faecales. turbidity of a 0.5 McFarland standard. The staples were placed on top of the agar and the plates were incubated at 35°C for 24 hours. As illustrated in the following table, only the silver coated staple of the present invention showed any bacteriostatic action showing a zone inhibition around the staple.

35		Stapha	ureus	Esche Co.	richia li	Pseudo Aerigi		Faec	•
40	Silver Plated	TSS Agar 11mm	M-H Agar 11mm	TSS Agar 6mm	M-H Agar	TSS Agar 22mm?	M-H Agar	TSS Agar	Agar
40	Stainless Steel	•••	•••	•••	•••	•••	•••	• • •	• • •
	Titanium	• • •	•••	• • •	• • •	•••	•••	•••	

WO 92/13491 PCT/US92/00209

5

10

5

In view of the above, it will be seen that the several objects of the invention are achieved and other advantageous results attained.

As various changes could be made in the above constructions without departing from the scope of the invention, it is intended that all matter contained in the above description or shown in the accompanying drawings shall be interpreted as illustrative and not in a limited sense.

. 5

30

WHAT IS CLAIMED IS:

- 1. An improved staple, wire suture, clip, or other metallic item of surgical hardware of the type made from a high strength metal such as stainless steel or titanium, the improvement comprising a silver coating on the surface of the hardware.
- The hardware according to claim I wherein the
 silver coating comprises silver plating.
 - 3. The hardware according to claim 1 wherein the silver coating comprises silver salts.
- 4. A staple, wire suture, clip, or other item of surgical hardware used to close a wound, made from a high strength metal to have a low profile design to minimize interference and disturbance of the wound, and having a bacteriostatic silver coating to reduce the risk of wound infection from the hardware.
 - 5. The hardware according to claim 4 wherein the silver coating comprises silver plating.
- 25 6. The hardware according to claim 4 wherein the silver coating comprises silver salts.
 - 7. A method of closing surgical wounds with reduced risk of infection comprising the step of closing the wound with a staple, wire suture, clip or other item of surgical hardware made from a high strength metal that has a silver coating.
- 8. The method according to claim 4 wherein the silver coating comprises silver plating.
 - 9. The method according to claim 4 wherein the silver coating comprises silver salts.

PCT/US92/00209

- 10. A surgical staple having bacteriostatic coating.
- 11. A surgical staple according to claim 1 wherein said bacteriostatic coating is silver.

F/G.1.






FIG. 2.



F/G.3.



F1G. 4.






FIG. 7.







International Application No

L CLASSI	FICATION OF SUBJ	ECT MATTER (If several classification	n symbols apply, indicate all) ⁶	
According	to International Paten	Classification (IPC) or to both Nationa	Classification and IPC	
Int.Cl	. 5 A61B17/0	64		
II. FIELDS	SEARCHED			
		Minimum Doc	ementation Searchof	
Classifica	tion System		Classification Symbols	·
Int.Cl	. 5	A61B	·	
		Documentation Searches ett to the Extent that such Documen	ner than Minimum Documentation his are Included in the Fields Searched ⁸	
				_
m. Docu	MENTS CONSIDER	ED TO BE RELEVANT		
Category °		ocument, ¹¹ with indication, where appro	priate, of the relevant passages 12	Relevant to Claim No. ¹³
х	EP,A,O see cla	206 024 (BECTON) 30 D 1ms 1,4,11,12,14	ecember 1986	1-11
A	EP,A,0 see abs	255 248 (MINNESOTA) 3 tract	February 1988	3,6,9
A	CH,A,65	4 738 (BLÄTTLER) 14 M	arch 1986	
A	WO,A,8	102 668 (BURFORD) 1 0	ctober 1981	
A	EP,A,O	328 421 (CULUMBIA) 16	August 1989	
A		046 715 (USSC) 3 Marc	**	
Α	EP,A,O	406 014 (ETHICON) 2 J	anuary 1991	
	:			İ
"A" do	al categories of cited do	peral state of the art which is not	"I" inter document published after the interns or priority date and not in conflict with it cited to maderstand the principle or theor	se application but
∞	exidered to be of partic	niar relevance lished on or after the international	invention "X" document of particular relevance; the cla	med invention
- 61	ing date current which may thro	cannot be considered novel or cannot be involve an inventive step	considered to	
Wh	ich is cited to establish ation or other special r	the publication date of another	"Y" document of particular relevance; the cla- cannot be considered to involve an invent	ive step when the
	coment referring to an her means	oral disciosure, use, exhibition or	document is combined with one or more of ments, such combination being obvious to	ther such docu- o a person skilled
"P" do		to the international filing date but e claimed	in the art. *A" document member of the same patent fan	nily
	IFICATION			
Date of the		the International Search	Date of Mailing of this International Sear	са вироп
	27 A	PRIL 1992	6. 05. 92)
Internations	al Searching Authority		Signature of Authorized Officer	2
	EUROPE	AN PATENT OFFICE	BARTON S.	7

ANNEX TO THE INTERNATIONAL SEARCH REPORT ON INTERNATIONAL PATENT APPLICATION NO. US 9200209 SA

56283

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information. 27/04/92

Patent document cited in search report	Publication date	Patent f	Publication date	
ED_4_0206024	30-12-86	US-A- 48	86505 1	2-12-89
EP-A-0206024 ·	30-12-00			9-06-89
				1-09-89
		110 0		1-12-86
				1-01-90
			02947 0	8-01-87
 EP-A-0255248	03-02-88	US-A- 47		1-03-88
			-	9-03-90
	•			8-01-88
•				9-01-91
		JP-A- 630	35260 1!	5-02-88
CH-A-654738	14-03-86	None		
ио-A-8102668	01-10-81			1-03-82
40 Y STOFFOO	VI I V V V V V V V V V V	EP-A, B 004		1-03-82
		WO-A- 81		L-10-81
		GB-A,B 201		7-10-81
				1-10-81
			, 0000	5-10-84
		US-A- 46	15705 07	7-10-86
P-A-0328421	16-08-89	US-A- 50		3-05 - 91
IF-M USEOTES	20 00 05			7-08-89
				2-01-90
		AU-A- 79	22991 0	3-10-91
P-A-0046715	03-03-82	AT-T-	,0.0	5-06-84
				1-03-82
		-	-	0-07-84
		DE 0 1-		1-02-85
				5-01-83
			-	1-03-82 1-10-83
		US-A- 441	07286 04	
P-A-0406014	02-01-91	,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,		3-01-91
				l-12-90
		JP-A- 300	56378 22 	2-03-91

E For more details about this annex : see Official Journal of the European Patent Office, No. 12/82